



TECHNICAL DATA SHEET

2883

Hot Melt Chips

Grade	:	2883
Appearance	:	Clear Yellow Chips
Softening Point	:	80°C
Viscosity (170°C)	:	8,500 CPS
Open Time	:	40 Sec.
Setting Time	:	20 Sec.
Heat Resistance	:	65°C
Operation Temp.	:	140 - 175°C
Product Usage	:	Plastic, PET, Glass, Ceramics