香港九龍灣常悅道 20 號環球工商大廈 10 樓 9 室 Room 9, 10/F. International Plaza, 20 Sheung Yuet Road, Kowloon Bay, H.K. Tel: 852-2751 8880 Fax: 852-2795 1625 Web Site: www.uea.com.hk E-mail: info@uea.com.hk

TECHNICAL DATA SHEET

CA GEL

Description ULTRABOND CA GEL is thixotropic gel ethyl cyanoacrylate

adhesive. Equivalent to Loctite's 409.

Application Ideal for non-running, non-dripping, vertical, porous, big

gap application.

Full Cure Speed Plastic : 20 - 50 seconds

Rubber : 10 - 25 seconds Metal : 40 - 100 seconds (can improved by ULTRABOND CS-1 Setter)

General Properties

Uncured monomer

Main Component Ethyl Cyanoacrylate

Appearance Clear Liquid

Specific gravity, 25°C 1.1

Viscosity 25°C (CPS)

Brookfield LV

Thixo Gel (35,000 CPS)

Spindle 2 @ 30 rpm

Flash point >92°C

Shelf life $(20^{\circ}C)$ months 6

Storage Under 10°C

(Stored in cool & dry place, unopened bottle & out of direct sunlight)

Cured Adhesive

Gap Filling 1 mm

Tensile Strength $25 \sim 30 \text{ N/mm}^2$

steel - steel ASTM D-2095

Tensile shear Strength

steel/steel ASTM D-1002

Service Temperature Range $-55 \sim 82^{\circ}C$

Full cure time 24 hours

Safety Direction

Danger, irritant

Avoid contact with eyes and skin, bonds skin in seconds. In case of eye contact, flush with plenty water for over 15 minutes and call a physician immediately. Use in well-ventilated place. Avoid contact clothing; it can cause very strong

CA-CA GEL-E - 1 -

^{**} All the information is provided on the basic in good faith, and is believed to be trustworthy but is for reference only. Adhesion is very complicated and the result of it is much dependent on the surface material, additives, releasing agents of the substrates and user's methods. UEA and its agents, dealers, distributors, directors and employees cannot accept any liability for the results whatsoever arising from the use of UEA's products due that the utilization of these products is simply out of UEA's control. The users are responsible for selecting the suitability of the products and methods of use.

香港九龍灣常悅道 20 號環球工商大廈 10 樓 9 室 Room 9, 10/F. International Plaza, 20 Sheung Yuet Road, Kowloon Bay, H.K. Tel: 852-2751 8880 Fax: 852-2795 1625 Web Site: www.uea.com.hk E-mail: info@uea.com.hk

TECHNICAL DATA SHEET

heat.

Application Direction

- The surfaces to be bonded should be clean and free of grease completely.
- ULTRABOND CD-1 debonder or acetone can treat excess Adhesive.
- If setting time is too long due to large gaps or low relative humidity. ULTRABOND CS-1 Setter can be used.
- If the porosity of surface is higher, higher viscosity type should be better.
- Difficult to bond plastics, like PE, PP, Silicone Rubber, ABS, TPR, EPDM's Adhesion, ULTRABOND CP-1 Primer should be applied firstly, then applied ULTRABOND super glue.