

速能化工貿易有限公司

ULTRA ENERGY ADHESIVE TRADING CO. LTD.

香港九龍灣常悅道 20 號環球工商大廈 10 樓 9 室 Room 9, 10/F. International Plaza, 20 Sheung Yuet Road, Kowloon Bay, H.K. Tel: 852-2751 8880 Fax: 852-2795 1625 Web Site: <u>www.uea.com.hk</u> E-mail: <u>info@uea.com.hk</u>

TECHNICAL DATA SHEET CA920

Description ULTRABOND CA920 is a low viscosity quick setting velocity ethyl cyanoacrylate adhesive. Equivalent to Loctite's 420.

Application Ideal for bonding plastics, rubber, metal.

| Full Cure Speed | Plastic | : 4 - 5 seconds |
|-----------------|--------------------|--|
| | Rubber | : 4 - 5 seconds |
| | Metal | : 8 - 15 seconds |
| | Wood | : 6 - 8 seconds |
| | (22℃, 50% relative | e humidity ASTM D1002, 0.1 N/mm2 tensile |
| | shear strength) | |

General Properties

| <u>Uncured monomer</u> | | |
|------------------------------|---|--|
| Main Component | Ethyl Cyanoacrylate | |
| Appearance | Clear Liquid | |
| Specific gravity, 25°C | 1.05 | |
| Viscosity 25°C (CPS) | 2-3 CPS | |
| Brookfield LV | Z-J CFS | |
| Spindle 20 30rpm | >82°C | |
| Flash point | 202 C | |
| Shelf life (20°C) months | 6 | |
| Storage | Under 10°C | |
| (Stored in cool & dry place, | unopened bottle & out of direct sunlight) | |

Cured Adhesive

| Gap Filling | 0.04 mm |
|---------------------------|-------------|
| Tensile Strength | 25-30 N/mm² |
| Steel - Steel ASTM D-2095 | |
| Tensile shear Strength | 15-26 N/mm² |
| Steel/ Steel ASTM D-1002 | |
| Service Temperature Range | -55 to 82°C |
| Full cure time | 24 hours |

Safety Direction

Danger, irritant

Avoid contact with eyes and skin, bonds skin in seconds. In case of eye contact, flush with plenty water for over 15 minutes; call a physician immediately. Use in well-ventilated place. Avoid contact clothing; it can cause very strong heat.

CA-CA920-E - 1 -

^{**} All the information is provided on the basic in good faith, and is believed to be trustworthy but is for reference only. Adhesion is very complicated and the result of it is much dependent on the surface material, additives, releasing agents of the substrates and user's methods. UEA and its agents, dealers, distributors, directors and employees cannot accept any liability for the results whatsoever arising from the use of UEA's products due that the utilization of these products is simply out of UEA's control. The users are responsible for selecting the suitability of the products and methods of use.



速 能 化 工 貿 易 有 限 公 司 ULTRA ENERGY ADHESIVE TRADING CO. LTD.

香港九龍灣常悅道 20 號環球工商大廈 10 樓 9 室 Room 9, 10/F. International Plaza, 20 Sheung Yuet Road, Kowloon Bay, H.K. Tel : 852-2751 8880 Fax : 852-2795 1625 Web Site : <u>www.uea.com.hk</u> E-mail : <u>info@uea.com.hk</u>

TECHNICAL DATA SHEET

Application Direction

- The surfaces to be bonded should be clean and free of grease completely.
- ULTRABOND CD-1 Debonder or acetone can treat excess Adhesive.
- If setting time is too long due to large gaps or low relative humidity. ULTRABOND CS-1 Setter can be used.
- If the porosity of surface is higher, higher viscosity type should be better.
- Difficult to bond plastics, like PE, PP, Silicone Rubber, ABS, TPR, EPDM's Adhesion, ULTRABOND CP-1 Primer should be applied firstly, then applied ULTRABOND super glue.

^{**} All the information is provided on the basic in good faith, and is believed to be trustworthy but is for reference only. Adhesion is very complicated and the result of it is much dependent on the surface material, additives, releasing agents of the substrates and user's methods. UEA and its agents, dealers, distributors, directors and employees cannot accept any liability for the results whatsoever arising from the use of UEA's products due that the utilization of these products is simply out of UEA's control. The users are responsible for selecting the suitability of the products and methods of use.